



PLUG ASSIST MATERIAL— TYPE: HYTAC- FLXT



FLXT Character	
Color	Dark green
Density	848 - 913 kg/m ³
Thermal conductivity	0.17 W/mK
Coefficient of thermal expansion	36 x 10 ⁻⁶ m/m/° C
Compressive strength	93 Mpa
Service temperature	176° C

HYTAC -- FLXT STANDARD SIZE

ROD standard size	Diameter		Length			
	INCH	MM	INCH	MM		
Hytac FLXT, 2.0 D x 24 L	2	51	24	610		
Hytac FLXT, 2.5 D x 24 L	2.5	63	24	610		
Hytac FLXT, 3.0 D x 24 L	3	76	24	610		
Hytac FLXT, 3.5 D x 24 L	3.5	89	24	610		
Hytac FLXT, 4.0 D x 24 L	4	102	24	610		
Hytac FLXT, 4.5 D x 24 L	4.5	114	24	610		
Hytac FLXT, 5.0 D x 24 L	5	127	24	610		
Hytac FLXT, 5.5 D x 24 L	5.5	140	24	610		
Hytac FLXT, 6.0 D x 24 L	6	152	24	610		
Hytac FLXT, 7.0 D x 24 L	7	178	24	610		
Hytac FLXT, 8.0 D x 24 L	8	203	24	610		
Hytac FLXT, 9.0 D x 12 L	8	229	12	305		
Hytact FLXT, 9.5 D x 12 L	9	221	12	305		
Hytac FLXT, 10 D x 12 L	9.5	241	12	305		
Hytac FLXT, 12 D x 12 L	10	254	12	305		
SHEET standard size	THICNESS		Length		Width	
	INCH	MM	INCH	MM	INCH	MM
Hytac FLXT Sht, 1.0 x 24 x 26	1.0	25.4	24	610	26	660
Hytac FLXT Sht, 1.5 x 24 x 26	1.5	38	24	610	26	660
Hytac FLXT Sht, 2.0 x 24 x 26	2.0	51	24	610	26	660
Hytac FLXT Sht, 2.5 x 24 x 26	2.5	64	24	610	26	660
Hytac FLXT Sht, 3.0 x 24 x 26	3.0	76	24	610	26	660
Hytac FLXT Sht, 3.5 x 24 x 26	3.5	89	24	610	26	660
Hytac FLXT Sht, 4.0 x 24 x 26	4.0	102	24	610	26	660
Hytac FLXT Sht, 4.5 x 24 x 26	4.5	114	24	610	26	660
Hytac FLXT Sht, 6.0 x 12 x 24	6.0	152	12	305	24	610
Hytac FLXT Sht, 6.0 x 24 x 26	6.0	152	24	610	26	660
Hytac FLXT Board, 1.0 x 24 x 60	1.0	25.4	24	610	60	1524
Hytac FLXT Board, 2.0 x 24 x 60	2.0	51	24	610	60	1524
Hytac FLXT Board, 2.5 x 24 x 60	2.5	64	24	610	60	1524
Hytac FLXT Board, 3.0 x 24 x 60	3.0	76	24	610	60	1524
Hytac FLXT Board, 4.0 x 24 x 60	4.0	102	24	610	60	1524
Hytac FLXT Board, 5.0 x 24 x 60	5.0	127	24	610	60	1524
Hytac FLXT Board, 6.0 x 24 x 60	6.0	152	24	610	60	1524